

Low Exothermic Reaction
Improved Color Stability
Fast Setting
Cross-Linked for Improved Craze Resistance



## INSTRUCTIONS

- 1. Clean and roughen denture area to be relined. Dry denture completely.
- Lubricate the labial and buccal surfaces within 1/8" of the peripheral border.
- Paint reline area with DuraLiner Bonding Liquid.
  This assures a chemical bond.
- 4. Recommended powder/liquid proportions:

Powder 10ml -shorter plastic vial Liquid 7ml -taller plastic vial

Add liquid to powder in mixing cup and stir thoroughly for 30 seconds.

- 5. Wait approximately 1 minute and apply mixture to denture.
- Insert denture in mouth and have patient close mouth lightly into occlusion.
- After approximately 3-4 minutes in the mouth, muscle-trim the borders, then remove the denture and trim the excess. Rinse the denture in cold tap water and reseat in patient's mouth.
- DuraLiner II sets in approximately 12 minutes when cured in the mouth. Remove denture after curing, trim any excess material and polish denture.
- To reduce residual taste, place denture in hot water for 10 minutes at 130° F / 55° C or in a pressure cooker at 130° F / 55° C for 10 minutes at 15 psi.

PACKAGE CONTAINS: 4 oz. Powder; 4 oz. Liquid





Reliance Dental Manufacturing, LLC • 5805 W. 117th Place • Alsip, IL 60803

European Representative: Kentzler-Kaschner Dental GMBH Muhlgraben 36d • D-73479 Ellwangen - Germany Tel: +49 7961 907305 • kkd.topdent.de